



Wir bestimmen Qualität!

CTL®-No 508207-1

[Article] PREMIUM BOMBER

[Colour] Maple

[Date] 07.05.2012

TEST REPORT

Test	Test Method / Standard		Value		Category
			Warp	Weft	
Tensile Strength	EN ISO 13934-1	N (%)	756 (17.4)	493 (24.8)	A/A-B
Tear Growth Strength	EN ISO 13937-3	N	70.3	34.8	A/B
Resistance to seam slippage	EN ISO 13936-2 180 N	mm	2.5	2.3	A/A
Abrasion Test	EN ISO 12947-1 EN ISO 12947-2	Revs.	95 000		A
Fastness to light	EN ISO 105-B02 Method 2	Grade	5		B
Fastness to rubbing	EN ISO 105-X12	Grade	dry	wet	A/A
			5	5	

CTL® GmbH


i.V. Heinz W. Eikelmann



CTL® GmbH
CHEMISCH-TECHNOLOGISCHES LABORATORIUM

Ningbo Matthew Synthetic Leather Co. Ltd.
Southern Section 345
315012 Ningbo Zhejiang

CTL®-Nr.



508207

[Artikelbezeichnung]

Premium Bomber

[Farbe]

Maple

Scheuerbeständigkeit nach Martindale		12 kPa Belastung gegen Crossbred	
Original	3000 Touren	Beschichtungsbruch	
			
		<u>95 000</u> Touren	
Reibechtheit		DIN EN ISO 105-X12	
	Trocken	Nass	
			
	Note 5	Note 5	