



Wir bestimmen Qualität!

CTL®-No.	516447-2
-----------------	-----------------

[Article Description]	OMEGA
[Colour]	CREAM
[Date]	29.08.2017

Test Results

Test	Test specification	Test result		
*Permanent creasing behaviour Original	acc. to DIN EN ISO 32100/ DIN 53359 100 000 cycles Sample shape: B	Lengthwise	Crosswise	Diagonal
		OK	OK	OK
*Permanent creasing behaviour after Hydrolysis acc. ISO 1419 35d 70°C 95-98% rel.AH	acc. to DIN EN ISO 32100/ DIN 53359/ 15 000 cycles Sample shape: B	Lengthwise	Crosswise	Diagonal
		OK	OK	OK
*Permanent creasing behaviour after Hydrolysis acc. ISO 1419 56d 70°C 95-98% rel.AH	acc. to DIN EN ISO 32100/ DIN 53359/ 15 000 cycles Sample shape: B	Lengthwise	Crosswise	Diagonal.
		OK	OK	OK
*Permanent creasing behaviour after Hydrolysis acc. ISO 1419 70d 70°C 95-98% rel.AH	acc. to DIN EN ISO 32100/ DIN 53359/ 15 000 cycles Sample shape: B	Lengthwise	Crosswise	Diagonal
		OK	OK	OK

CTL® GmbH

i.V. Lothar Dornau

Legende: DL = Detection Limit, n.d. = not detectable, --- = testing not relevant

Legende fibres: WO – Wool // PAN – Polyacryl // PES – Polyester // PA – Polyamid // CO – Cotton // CA – Acetat

► 2/2

[Address] Carl-Bertelsmann-Str. 66
33332 Gütersloh, Germany
[Managing Director] Kerry-Luise Prior
[Based in] Bielefeld
[Register of Companies] AG Bielefeld, HRB 35-412
[USt-IdNr.] DE 176 26 5000

[fon] +49 5241 300 68 20
[fax] +49 5241 306 94 40
[mail] labor_gtl@ctl-mails.de
[Homepage] ctl-esteem.net
ctl-automobil.de

[Bank] Sparkasse Gütersloh
Konrad-Adenauer-Platz 1
33330 Gütersloh, GERMANY
[SWIFT/BIC] WELADED 1 GTL
[IBAN] DE 56 4785 0065 0004 0124 99



Wir bestimmen Qualität!

CTL®-No. **516447-1**

[Article Description] **OMEGA**

[Colour] **WHITE**

[Date] **29.08.2017**

Test Results

Test	Test specification	Test result		
*Permanent creasing behaviour Original	acc. to DIN EN ISO 32100/ DIN 53359 100 000 cycles Sample shape: B	Lengthwise OK	Crosswise OK	Diagonal OK
*Permanent creasing behaviour after Hydrolysis acc. ISO 1419 35d 70°C 95-98% rel.AH	acc. to DIN EN ISO 32100/ DIN 53359/ 15 000 cycles Sample shape: B	Lengthwise OK	Crosswise OK	Diagonal OK
*Permanent creasing behaviour after Hydrolysis acc. ISO 1419 56d 70°C 95-98% rel.AH	acc. to DIN EN ISO 32100/ DIN 53359/ 15 000 cycles Sample shape: B	Lengthwise OK	Crosswise OK	Diagonal OK
*Permanent creasing behaviour after Hydrolysis acc. ISO 1419 70d 70°C 95-98% rel.AH	acc. to DIN EN ISO 32100/ DIN 53359/ 15 000 cycles Sample shape: B	Lengthwise OK	Crosswise OK	Diagonal OK

CTL® GmbH

i.V. Lothar Dornau

Legende: DL = Detection Limit, n.d. = not detectable, --- = testing not relevant

Legende fibres: WO – Wool // PAN – Polyacryl // PES – Polyester // PA – Polyamid // CO – Cotton // CA - Acetat

2/2

[Address] Carl-Bertelsmann-Str. 66
33332 Gütersloh, Germany
[Managing Director] Kerry-Luise Prior
[Based in] Bielefeld
[Register of Companies] AG Bielefeld, HRB 35-412
[USt-IdNr.] DE 176 26 5000

[fon] +49 5241 300 68 20
[fax] +49 5241 306 94 40
[mail] labor_gt@ctl-mails.de
[Homepage] ctl-esteem.net
ctl-automobil.de

[Bank] Sparkasse Gütersloh
Konrad-Adenauer-Platz 1
33330 Gütersloh, GERMANY
[SWIFT/BIC] WELADED 1 GTL
[IBAN] DE 56 4785 0065 0004 0124 99